

INDION® 225 Na F

Description

INDION 225 NaF is a strongly acidic cation exchange resin containing sulphonic acid groups. It is specially designed for the treatment of foodstuffs, beverages, potable water and water used in the processing of food. Its specification is in compliance with the U.S. Food and Drug Administration Code of Federal Regulations

section 21, paragraph 173.25, for use in the treatment of foods for human consumption. The resin is extremely robust and has excellent physical and chemical characteristics. It is supplied in moist condition in sodium form.

Characteristics

Appearance	:	Golden yellow beads
Matrix	:	Styrene divinylbenzene copolymer
Functional Group	:	Sulphonic acid
Ionic form as supplied	:	Sodium
Total exchange capacity	:	2.0 meq/ml, minimum
Moisture holding capacity	:	43 - 50 %
Shipping weight *	:	830 kg/m ³ , approximately
Particle size range	:	0.3 to 1.2 mm
> 1.2 mm	:	5.0%, maximum
< 0.3 mm	:	1.0%, maximum
Uniformity co-efficient	:	1.7, maximum
Effective size	:	0.45 to 0.55 mm
Minimum Flow Greater than or equal to	:	0.24 gpm/ft ³
	:	1.93 LPH/Ltr Resin
	:	1.93 BV/hr
Maximum operating temperature	:	140° C
Operating pH range	:	0 to 14
Resistance to reducing agents	:	Good
Resistance to oxidizing agents	:	Generally good, chlorine should be absent
Organic extractives	:	1 mg/l maximum in deionised water
(As per USFDA 21 CFR 173.25)	:	1 mg/l maximum in 15% v/v ethanol Solution

Impurities

Iron	:	100 mg/l maximum as Fe
Heavy Metals	:	20 mg/l maximum as Pb
Arsenic	:	3 mg/l maximum as As

* Weight of resin, as supplied, occupying 1 m³ in a unit after backwashing and draining.

Recommended usage

It is highly recommended that the INDION 225NaF after charging in the service vessel should be thoroughly washed with 20 bv* of deionised water, to ensure that the organic leachables are well within the limits. It may be noted that this procedure is to be carried out only after initial charge or in case the service vessel is out of operation for a long period.

* 1 bv = 1 m³ per m³ of resin volume

Packing

HDPE Lined bags	25/ 50 lts	LDPE bags	1 cft / 25 lts
Super sack	1000 lts	Super sack	35 cft
MS drums with liner bags	180 lts	Fiber drums with liner bags	7 cft



CONFORMANCE STATEMENT:

This product conforms to NSF / ANSI Standard 61 and is certified with GOLD SEAL from WQA

INDION range of ion exchange resins are produced in a state of the art ISO 9001 and ISO 14001 certified manufacturing facilities at Ankleshwar, in the state of Gujarat in India. This product data sheet (issue 09/2008) replaces previous issues.

To the best of our knowledge the information contained in this publication is accurate. Ion Exchange (India) Ltd. maintains a policy of continuous development and reserves the right to amend the information given herein without notice.

INDION is the registered trademark of Ion Exchange (India) Ltd.



CORPORATE OFFICE

Ion House, Dr. E. Moses Road, Mahalaxmi, Mumbai 400 011
Tel: 022-3989 0909 Fax: 022-2493 8737
E-mail: ieil@ionexchange.co.in; hocro@ionexchange.co.in

INTERNATIONAL DIVISION

R-14, T.T.C MIDC, Thane-Belapur Road, Rabale, Navi Mumbai 400 705
Tel: 022-3989 0909/3047 2400 Fax: 022-2769 7918
E-mail: rabcrointl@ionexchange.co.in; export.sales@ionexchange.co.in

REGIONAL OFFICES

- **Chennai** - Tel: 044-3989 0909/3910 2900 Fax: 044-2815 3361
E-mail: checro@ionexchange.co.in
- **Delhi** - Tel: 011-3989 0909/3054 3200 Fax: 011-2577 4837
E-mail: delcro@ionexchange.co.in
- **Kolkata** - Tel: 033-3989 0909/3043 3400 Fax: 033-2400 4345
E-mail: calcro@ionexchange.co.in
- **Vashi** - Tel: 022-3989 0909/3913 2300 Fax: 022-2788 9839
E-mail: mumcro@ionexchange.co.in

Storage

INDION 225 NaF resin beads must never be allowed to become dry. Therefore always store resin bags in the shade.

Safety

Acid and alkali solutions used for regeneration are corrosive and should be handled in a manner that will prevent eye and skin contact. If any oxidising agents are used, necessary safety precautions should be observed to avoid accidents and damage to the resin.

BRANCH OFFICES

- **Bangaluru** - Tel:-080-2204 2888
E-mail: bngcro@ionexchange.co.in
- **Bhubaneshwar** - Tel: 0674-326 9525
E-mail: bbsr@ionexchange.co.in
- **Chandigarh** - Tel: 0172-274 5011 Fax: 0172-274 4594
E-mail: delcro@ionexchange.co.in
- **Hyderabad** - Tel: 040-3066 3101/02/03 Fax: 040-3066 3104
E-mail: hydicro@ionexchange.co.in
- **Lucknow** - Tel: 0522-301 3401/02 Fax: 0522- 301 3401
E-mail: luk.general@ionexchange.co.in
- **Vadodara** - Tel: 0265-239 6506/6507 Fax: 0265-239 8508
E-mail: brdcro@ionexchange.co.in
- **Vizag** - Tel: 0891-324 6253
E-mail: sales.vizag@ionexchange.co.in

FACTORIES: • Ankleshwar • Hosur • Patancheru • Rabale • Verna

ALL INDIA NETWORK OF SERVICE COMPANIES AND DEALERS

Visit us at : www.ionindia.com