

INDION® GS 400

Description

INDION GS 400 is strong base Type II anion exchange resin, based on cross linked polystyrene matrix with benzyl dimethyl ethanol amine functional groups. It has a gel structure with high physical strength. INDION GS 400 has high operating exchange capacity & excellent regeneration efficiency.

INDION GS 400 is recommended as the anion exchange resin in the second stage of a de-ionising pair with the cation exchange resin INDION 225 H in the first stage.

INDION GS 400 is particularly recommended for use in a two stage de-ionising plant for removal of mineral acid anions and some silica, while keeping the running cost down. If treated water with lowest possible level of residual silica is desired, this two stage treatment should be followed by mixed bed de-ionising using a strong acid cation resin INDION 225 H and a strong base Type I anion resin INDION GS 300.

Characteristics

Appearance	:	Pale yellow translucent beads
Matrix	:	Styrene divinylbenzene copolymer
Functional Group	:	Benzyl dimethyl ethanolamine
Ionic form as supplied	:	Chloride
Total exchange capacity	:	1.2 meq/ml, minimum
Moisture holding capacity	:	39 - 46 %
Shipping weight *	:	670 kg/m ³ , approximately
Particle size range	:	0.3 to 1.2 mm
> 1.2 mm	:	5.0%, maximum
< 0.3 mm	:	1.0%, maximum
Uniformity co-efficient	:	1.7, maximum
Effective size	:	0.45 to 0.55 mm
Maximum operating temperature	:	40°C in OH form 75°C in Cl form
Operating pH range	:	0 to 14
Volume change	:	Cl to OH, 10 - 15 % maximum
Resistance to reducing agents	:	Good
Resistance to oxidizing agents	:	Generally good, chlorine should be absent

*Weight of resin, as supplied, occupying 1 m³ in a unit after backwashing and draining.

Two stage de-ionising

This technical literature describes typical operating data and operating exchange capacities of INDION GS 400 when used:

- Two stage de-ionising (Co-flow and countercurrent regeneration technique.)

Typical operating data

Two stage/multiple stage de-ionising	Co-flow regeneration	Counter current regeneration (CCR)
Bed depth	0.75 - 1.50 m	1.0 m, minimum
Treatment flowrate.....	60m ³ /h m ² , maximum	60m ³ /h m ² , maximum
Pressure loss.....	Refer Figure 9	Refer Figure 9
Bed expansion	Refer Figure 10	Refer Figure 10
Backwash.....	3 m ³ /h m ² for 5 min or till effluent is clear.	3 m ³ /h m ² till effluent is clear *
Regenerant	Sodium hydroxide (2 - 4% w/v)	Sodium hydroxide (2 - 4% w/v)
Regenerant flowrate	4.5 - 18 m ³ /h m ²	4.5 -18 m ³ /h m ²
Regenerant injection time	30 minutes	30 minutes
Slow rinse	2.5 to 3 bv at regenerant flow rate	2 to 3 bv at regenerant flow rate
Final rinse.....	6 bv at service flow rate	5 bv at service flow rate

* After set number of regeneration 1bv (bed volume) = 1 m³ fluid/m³ of resin

Operating exchange Capacity

Two stage de-ionising


Indion GS 400 is recommended as the anion exchanger in the second stage of a de-ionising pair with INDION 225 H cation exchange resin in the first stage.

Indion GS 400 is particularly recommended for use in a two-stage de-ionising plant for the removal of mineral acid anions and some silica, while keeping running costs down. If treated water with the lowest possible level of residual silica is required, two stage treatment should be followed by mixed bed de-ionising using a strong acid cation resin INDION 225H & Type I strong base anion exchange resin such as INDION GS 300.

The Operating exchange capacity of INDION GS 400 in two stage de-ionising system is dependent upon:

- The regeneration level employed and the composition of water to be treated, specifically the concentration of mineral acid anions ($SO_4/EMA\%$)
- The operating exchange capacities are shown as a function of regeneration level for various percentages of SO_4/EMA in Figure 1 for co-flow regeneration and in Figure 2 for counter current regeneration.
- Silica content ($SiO_2/TA\%$) in water to be treated.

- Refer Figure 3 for capacity deduction data to be applied to basic operating exchange capacities in co-flow and counter current mode obtained from Figure 1 and 2 respectively.
- In co-flow mode if feed SiO_2/TA ratio is 40% or more, then the operating capacity values obtained from Figure 1, should be derated further by 20 per cent and the capacity deduction from Figure 3 increased by 20 percent.
- Exhaustion time
The operating capacity data is related to exhaustion time greater than 10 hours. Figure 4 shows the correction factor to be applied on operating capacity (after capacity deduction for silica content) with exhaustion time for both co-flow and counter current regeneration.



Treated water quality

Two stage de-ionising

The quality of treated water from a two stage deionising plant using INDION GS 400 as the anion exchanger is determined by:

- Regeneration level employed
- Temperature of the regenerant
- Level of sodium ion leakage from the cation exchanger
- Silica to total anion ratio of water fed to the anion exchanger

Sodium ions leaking from the cation exchanger are converted to NaOH as the water passes through the anion exchanger.



Each ppm of sodium leakage, expressed as CaCO_3 , increases conductivity of the water leaving the anion exchanger by approximately 5 microsiemens/cm at 20°C.




The values for residual silica in the treated water at various regeneration levels and temperatures can be obtained from :



Figure 5 & 6 Co-flow regeneration



Figure 7 & 8 Counter current regeneration

These values assume zero sodium slip and for every ppm of sodium leakage as CaCO_3 , the residual silica increases by 25%.









Use of good quality regenerants

All ion exchange resins are subject to fouling and blockage of active groups by precipitated iron. Hence the iron content in the feed water should be low and the regenerant sodium hydroxide must be essentially free from iron and heavy metals. All resins, especially the anion exchangers are prone to oxidative attack resulting in problems such as loss of capacity, resin clumping, etc. Therefore sodium hydroxide should have as low a chlorate content as possible. Good quality regenerant of technical or chemically pure grade should be used to obtain best results.

Packing

HDPE lined bags	25/50 lts	LDPE bags	1 cft/25 lts
Super sack	1000 lts	Super sack	35 cft
MS drums	180 lts	Fiber drums	7 cft
with liner bags		with liner bags	

INDION range of Ion Exchange resins are produced in a state of the art ISO 9001 and ISO 14001 certified manufacturing facilities at Ankleshwar, in the state of Gujarat in India. This product data sheet (issue 09/2008) replaces previous issues.

To the best of our knowledge the information contained in this publication is accurate. Ion Exchange (India) Ltd. maintains a policy of continuous development and reserves the right to amend the information given herein without notice.

INDION is the registered trademark



CORPORATE OFFICE

Tiecicon House, Dr. E. Moses Road, Mahalaxmi, Mumbai 400 011
Tel: 022-3989 0909 Fax: 022-2493 8737
E-mail: ieil@ionexchange.co.in ; hocro@ionexchange.co.in

INTERNATIONAL DIVISION

R-14, T.T.C MIDC, Thane-Belapur Road, Rabale, Navi Mumbai 400 705
Tel: 022-3989 0909/3047 2400 Fax: 022-2769 7918
E-mail: rabcrointl@ionexchange.co.in; export.sales@ionexchange.co.in

REGIONAL OFFICES

- **Chennai** - Tel: 044-3910 2900/ 3989 0909 Fax: 044-2815 3361
E-mail: checro@ionexchange.co.in
- **Delhi** - Tel: 011-3989 0909/3054 3200 Fax: 011-2577 4837
E-mail: delcro@ionexchange.co.in
- **Kolkata** - Tel: 033-3989 0909/3043 3400 Fax: 033-2400 4345
E-mail: calcro@ionexchange.co.in
- **Vashi** - Tel: 022-3989 0909/3913 2300 Fax: 022-2788 9839
E-mail: mumcro@ionexchange.co.in

Storage

Ion exchange resins require proper care at all times. The resin must never be allowed to become dry.

Regularly open the plastic bags and check the condition of the resin when in storage. If not moist, add enough clean demineralised water and keep it in completely moist condition. Always keep the resin drum in the shade. Recommended storage temperature is between 20° C and 40° C.

Safety

Acid and alkali solutions are corrosive and should be handled in a manner that will prevent eye and skin contact. If any oxidising agents are used, necessary safety precautions should be observed to avoid accidents and damage to the resin.

BRANCH OFFICES

- **Bangalore** - Tel:-080-3251 6205, Cell:09341247700
E-mail: bngcro@ionexchange.co.in
- **Chandigarh** - Tel: 0172-274 5011 Fax: 0172-274 4594
E-mail: delcro@ionexchange.co.in
- **Hyderabad** - Tel: 040-3066 3101/02/03 Fax: 040-3066 3104
E-mail: hydrcro@ionexchange.co.in
- **Lucknow** - Tel: 0522-301 3401/02 Fax: 0522- 301 3401
E-mail: luk.general@ionexchange.co.in
- **Pune** - Tel: 020-3062 6160 Fax: 020-2714 6109
E-mail: pun.general@ionexchange.co.in
- **Vadodara** - Tel: 0265-239 6506/6507 Fax: 0265-239 8508
E-mail: brdcro@ionexchange.co.in
- **Vizag** - Tel: 0891-324 6253
E-mail: sales.vizag@ionexchange.co.in

FACTORIES

• Ankleshwar • Hosur • Patancheru • Rabale • Verna

ALL INDIA NETWORK OF SERVICE COMPANIES AND DEALERS

Visit us at : www.ionindia.com