

INDION® MB 115

Description

INDION MB 115 is a mixed bed ion exchange resin. It is a mixture of highly purified and super regenerated Strong acid cation and strong base anion resins in 40 : 60 volume ratio.

Applications

INDION MB 115 is recommended in any non regenerable mixed bed application where reliable production of the highest quality water is required and where "as supplied" resin must have an absolute minimum of ionic and nonionic contamination.

Characteristics

Physical

Appearance	:	Spherical beads
Shipping weight *	:	710 kg/m ³ , approximately
Particle size range	:	0.3 to 1.2 mm
> 1.2 mm	:	5.0 %, maximum
< 0.3 mm	:	0.5 %, maximum
Uniformity co-efficient	:	1.8, maximum
Effective size	:	0.45 to 0.60 mm
Microscopic Examination	:	Surface cracks not more than 5 %

Chemical

Matrix
Type
Functional Group
Total exchange capacity
Ionic conversion

Cation resin

Crosslinked polystyrene
Gel
Sulphonic acid
1.8 meq/ml
99 % minimum in H form

Anion resin

Crosslinked polystyrene
Gel
Quaternary ammonium
1.0 meq/ml
90 % minimum in OH form
1 % maximum in Cl form
5% maximum in CO₃ form

Moisture holding capacity
Thermal stability

50 - 55 %
Up to 120° C

60 % maximum
Up to 60° C

Chemical stability

: Stable in pH range 0 - 14
Resistant to oxidizing and reducing agents

* Weight of resin, as supplied, occupying 1 m³ in a unit after backwashing and draining.

Variants

INDION MB 115 resin is also available with the additional feature of colour change at exhaustion. Three variants of this colour indicating Indion MB 115 are available :

Indion MB 115 (GVI) Green to Violet

Indion MB 115 (BYI) Blue to Yellow

Indion MB 115 (GOI) Green to Orange

Packing

PVC Jars with inner liner bags	5 / 6 lts
LDPE lined bags	0.5 cft / 1 cft / 25 lts
HDPE lined bags	25 / 50 lts
HDPE drums	50 / 100 / 180 lts

Storage

Ion exchange resins require proper care at all times. Resins must never be allowed to become dry. Resins should therefore be always kept in shade. Since INDION MB 115 is supplied in highly regenerated condition, any exposure to atmospheric air must be avoided as this will convert it to the carbonate form. The resin packing should not be opened during storage.

Safety

Acid and alkali solutions used for regeneration are corrosive and should be handled in a manner that will prevent eye and skin contact. If any oxidising agents are used, necessary safety precautions should be observed to avoid accidents and damage to the resin.

INDION range of Ion Exchange resins are produced in a state of the art ISO 9001 and ISO 14001 certified manufacturing facilities at Ankleshwar, in the state of Gujarat in India. This product data sheet (issue 09/2008) replaces previous issues.

To the best of our knowledge the information contained in this publication is accurate. Ion Exchange (India) Ltd. maintains a policy of continuous development and reserves the right to amend the information given herein without notice.

INDION is the registered trademark



CORPORATE OFFICE

Tiecicon House, Dr. E. Moses Road, Mahalaxmi, Mumbai 400 011
Tel: 022-3989 0909 Fax: 022-2493 8737
E-mail: ieil@ionexchange.co.in ; hocro@ionexchange.co.in

INTERNATIONAL DIVISION

R-14, T.T.C MIDC, Thane-Belapur Road, Rabale, Navi Mumbai 400 705
Tel: 022-3989 0909/3047 2400 Fax: 022-2769 7918
E-mail: rabcrointl@ionexchange.co.in; export.sales@ionexchange.co.in

REGIONAL OFFICES

- **Chennai** - Tel: 044-3910 2900/ 3989 0909 Fax: 044-2815 3361
E-mail: checro@ionexchange.co.in
- **Delhi** - Tel: 011-3989 0909/3054 3200 Fax: 011-2577 4837
E-mail: delcro@ionexchange.co.in
- **Kolkata** - Tel: 033-3989 0909/3043 3400 Fax: 033-2400 4345
E-mail: calcro@ionexchange.co.in
- **Vashi** - Tel: 022-3989 0909/3913 2300 Fax: 022-2788 9839
E-mail: mumcro@ionexchange.co.in

BRANCH OFFICES

- **Bangalore** - Tel:-080-3251 6205, Cell:09341247700
E-mail: bngcro@ionexchange.co.in
- **Chandigarh** - Tel: 0172-274 5011 Fax: 0172-274 4594
E-mail: delcro@ionexchange.co.in
- **Hyderabad** - Tel: 040-3066 3101/02/03 Fax: 040-3066 3104
E-mail: hydrcro@ionexchange.co.in
- **Lucknow** - Tel: 0522-301 3401/02 Fax: 0522- 301 3401
E-mail: luk.general@ionexchange.co.in
- **Pune** - Tel: 020-3062 6160 Fax: 020-2714 6109
E-mail: pun.general@ionexchange.co.in
- **Vadodara** - Tel: 0265-239 6506/6507 Fax: 0265-239 8508
E-mail: brdcro@ionexchange.co.in
- **Vizag** - Tel: 0891-324 6253
E-mail: sales.vizag@ionexchange.co.in

FACTORIES

• Ankleshwar • Hosur • Patancheru • Rabale • Verna

ALL INDIA NETWORK OF SERVICE COMPANIES AND DEALERS

Visit us at : www.ionindia.com