

INDION® 810

Description

INDION 810 is a macroporous strongly basic Type 1 anion exchange resin. It is a high capacity, new generation resin based on crosslinked polystyrene matrix and has quaternary ammonium functional groups.

INDION 810 is produced by a unique manufacturing technique, which gives it the optimum porosity and improved kinetics. It gives higher operating exchange capacity due to greater utilisation of the exchange sites as compared to other conventional macroporous resins. This feature, combined with its high basicity, permits absorption of large sized soluble organic molecules and their subsequent elution during regeneration. Thus, while INDION 810 ensures

complete removal of soluble organics from the water, it exhibits excellent resistance to organic fouling as compared to other conventional resins.

INDION 810 has very good stability against physical and chemical attrition. This results in lesser fines generation and therefore higher operating life for the resin.

INDION 810 is generally employed in demineralising applications of raw water containing high organic levels and also for use under rigorous conditions such as in condensate polishing. INDION 810 is recommended for use in the anion column as well as in the mixed bed column where it can act as an efficient polisher in combination with strong acid cation exchange resin INDION 225 H.

Characteristics

Appearance	:	Off white to brown opaque beads
Matrix	:	Styrene divinyl benzene copolymer
Functional Group	:	Benzyl trimethyl amine
Ionic form as supplied	:	Chloride
Total exchange capacity	:	1.0 meq/ml, minimum
Moisture holding capacity	:	56 - 63 %
Shipping weight *	:	650 kg/m ³ , approximately
Particle size range	:	0.3 to 1.2 mm
> 1.2 mm	:	5.0%, maximum
< 0.3 mm	:	1.0%, maximum
Uniformity co-efficient	:	1.7, maximum
Effective size	:	0.45 to 0.55 mm
Maximum operating temperature	:	60° C in OH form 90° C in Cl form
Operating pH range	:	0 to 14
Volume change	:	Cl to OH, 15 - 20 %
Resistance to reducing agents	:	Good
Resistance to oxidizing agents	:	Generally good, chlorine should be absent

* Weight of resin, as supplied, occupying 1 m³ in a unit after backwashing and draining.

Packing

HDPE Lined bags	25/ 50 lts	LDPE bags	1 cft / 25 lts
Super sack	1000 lts	Super sack	35 cft
MS drums		Fiber drums	
with liner bags	180 lts	with liner bags	7 cft

Storage

Ion exchange resins require proper care at all times. The resins must never be allowed to become dry. Regularly open the plastic bags and check the condition of the resin when in storage. If not moist, add enough

clean demineralised water and keep it in completely moist condition. Always keep the resin in shade. Recommended storage temperature is between 20° C and 40° C.

Safety

Acid and alkali solutions used for regeneration are corrosive and should be handled in a manner that will prevent eye and skin contact. If any oxidising agents are used, necessary safety precautions should be observed to avoid accidents and damage to the resin.

INDION range of Ion Exchange resins are produced in a state-of-the-art ISO 9001 and ISO 14001 certified manufacturing facilities at Ankleshwar, in the state of Gujarat in India.

To the best of our knowledge the information contained in this publication is accurate. Ion Exchange (India) Ltd. maintains a policy of continuous development and reserves the right to amend the information given herein without notice.

INDION is the registered trademark of Ion Exchange (India) Ltd.



CORPORATE OFFICE

Ion House, Dr. E. Moses Road, Mahalaxmi, Mumbai 400 011
Tel: 022-3989 0909 Fax: 022-2493 8737
E-mail: ieil@ionexchange.co.in

INTERNATIONAL DIVISION

R-14, T.T.C MIDC, Thane-Belapur Road, Rabale, Navi Mumbai 400 701
Tel: 022-3989 0909/3047 2400 Fax: 022-2769 7918
E-mail: rabcrointl@ionexchange.co.in; export.sales@ionexchange.co.in

REGIONAL OFFICES

- Chennai - Tel: 044-3989 0909/3910 2900 Fax: 044-2815 3361
E-mail: checro@ionexchange.co.in
- Delhi - Tel: 011-3989 0909/3054 3200 Fax: 011-2577 4837
E-mail: delcro@ionexchange.co.in
- Kolkata - Tel: 033-3989 0909/3043 3400 Fax: 033-2400 4345
E-mail: calcro@ionexchange.co.in
- Vashi - Tel: 022-3989 0909/3913 2300 Fax: 022-2788 9839
E-mail: mumcro@ionexchange.co.in

BRANCH OFFICES

- Bengaluru - Tel: 080-2204 2888
E-mail: bngcro@ionexchange.co.in
- Bhubaneswar - Tel: 0674-326 9525
E-mail: bbsr@ionexchange.co.in
- Chandigarh - Tel: 0172-274 5011 Fax: 0172-274 4594
E-mail: delcro@ionexchange.co.in
- Hyderabad - Tel: 040-3066 3101/02/03 Fax: 040-3066 3104
E-mail: hydcro@ionexchange.co.in
- Lucknow - Tel: 0522-301 3401/02 Fax: 0522-301 3401
E-mail: luk.general@ionexchange.co.in
- Vadodara - Tel: 0265-302 7489/90 Fax: 0265-239 8508
E-mail: brdcro@ionexchange.co.in
- Visakhapatnam - Tel: 0891-324 6253
E-mail: sales.vizag@ionexchange.co.in

FACTORIES : Ankleshwar • Hosur • Patancheru • Rabale • Verna
ALL INDIA SERVICE AND DEALER NETWORK

Visit us at : www.ionindia.com