

INDION® GS 80

Description

INDION GS 80 is a strongly basic anion exchange resin. It has a crosslinked polystyrene matrix and a quaternary ammonium functionality. INDION GS 80

has unique functional groups on its matrix which helps it to be used for oxygen scavenging applications. This ion exchanger is supplied in fully hydrated condition.

Characteristics

Appearance	:	Moist translucent, dark brown to black coloured spherical beads
Matrix	:	Gel structure
Ionic Form as supplied	:	Sulphite (SO ₃) form
Exchange capacity	:	0.8 meq/ml (minimum) of wet resin, SO ₃ form Exchange sites in SO ₃ form minimum 80% Exchange sites in Cl form maximum 5%
Moisture content (in Cl form)	:	47 - 55 % w/w
Particle size range	:	0.3 to 1.2 mm
Fines content passing through 300 micron sieve (no.30 IS)	:	1.0% v/v maximum
Chemical Nature	:	Strongly basic with Quaternary Ammonium functional groups
Uniformity co-efficient	:	1.8 maximum
Effective size	:	0.45 to 0.55 mm

Packing

HDPE Lined bags	25/ 50 lts	LDPE bags	1 cft / 25 lts
Super sack	1000 lts	Super sack	35 cft
MS drums		Fiber drums	
with liner bags	180 lts	with liner bags	7 cft
HDPE drums	50/100/180 lts		

Storage

Ion exchange resins require proper care at all times. The resins must never be allowed to become dry. The

resin should therefore be always kept in the shade. Since INDION GS 80 is supplied in Sulphite form, which has a tendency to absorb Oxygen, exposure to atmospheric air must be avoided, as this will convert it to the Sulphate form. The resin should therefore be kept in tightly closed condition.

Safety precautions

If any oxidizing agents are used, necessary safety precautions should be observed to avoid accidents and damaged to the resin.

INDION range of Ion Exchange resins are produced in a state-of-the-art ISO 9001 and ISO 14001 certified manufacturing facilities at Ankleshwar, in the state of Gujarat in India.

To the best of our knowledge the information contained in this publication is accurate. Ion Exchange (India) Ltd. maintains a policy of continuous development and reserves the right to amend the information given herein without notice.

INDION is the registered trademark of Ion Exchange (India) Ltd.



CORPORATE OFFICE

Ion House, Dr. E. Moses Road, Mahalaxmi, Mumbai 400 011
Tel: 022-3989 0909/3047 2400 Fax: 022-2493 8737
E-mail: ieil@ionexchange.co.in

INTERNATIONAL DIVISION

R-14, T.T.C MIDC, Thane-Belapur Road, Rabale, Navi Mumbai 400 701
Tel: 022-3989 0909/3047 2400 Fax: 022-2769 7918
E-mail: rabcrointl@ionexchange.co.in; export.sales@ionexchange.co.in

REGIONAL OFFICES

- Chennai - Tel: 044-3989 0909/3910 2900 Fax: 044-2815 3361
E-mail: checro@ionexchange.co.in
- Delhi - Tel: 011-3989 0909/3054 3200 Fax: 011-2577 4837
E-mail: delcro@ionexchange.co.in
- Kolkata - Tel: 033-3989 0909/3043 3400 Fax: 033-2400 4345
E-mail: calcro@ionexchange.co.in
- Vashi - Tel: 022-3989 0909/3913 2300 Fax: 022-2788 9839
E-mail: mumcro@ionexchange.co.in

BRANCH OFFICES

- Bengaluru - Tel: 080-2204 2888
E-mail: bngcro@ionexchange.co.in
- Bhubaneswar - Tel: 0674-326 9525
E-mail: bbsr@ionexchange.co.in
- Chandigarh - Tel: 0172-274 5011 Fax: 0172-274 4594
E-mail: delcro@ionexchange.co.in
- Hyderabad - Tel: 040-3066 3101/02/03 Fax: 040-3066 3104
E-mail: hydcro@ionexchange.co.in
- Lucknow - Tel: 0522-301 3401/02 Fax: 0522- 301 3401
E-mail: luk.general@ionexchange.co.in
- Vadodara - Tel: 0265-302 7489/90 Fax: 0265-239 8508
E-mail: brdcro@ionexchange.co.in
- Vishakhapatnam - Tel: 0891-324 6253
E-mail: sales.vizag@ionexchange.co.in

FACTORIES : Ankleshwar • Hosur • Patancheru • Rabale • Verna
ALL INDIA SERVICE AND DEALER NETWORK

Visit us at : www.ionindia.com